

GLITTER

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	350 microns	Adhesive polyester	REACH n° 1907/2006/EU

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS ↓			TRANSFER SETTINGS ↓			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	60°	120 gf	20 cm/sec	15 seconds	160°C (320°F)	Medium (2,5/3,5 bar)	hot/cold

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier hot/cold

PRODUCT HIGHLIGHTS

- easy to cut and weed
- perfect for trendy or fashion items
- "WOW" effect

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, inside-out	YES inside-out	NO	YES	Up to 2 year	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our Sales Office.