

# STRIPFLOCK PRO

## SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	500 microns	Adhesive polyester	REACH n° 1907/2006/EU 

## APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS ↓			TRANSFER SETTINGS ↓			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	60°	80 gf	15 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5)	warm

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier warm

### PRODUCT HIGHLIGHTS

- easy to cut and weed
- soft, velvet feel
- embroidery look

**NOTE:** Stripflock Pro cannot be layered on itself. We highly recommend to perform a test before launching a production.

## CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 year	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on [www.siser.com](http://www.siser.com). For further information, please contact our Sales Office.